

DATA SHEET

3C30

Material specification

Supersedes data of February 2002

2004 Sep 01




Material specification

3C30

3C30 SPECIFICATIONS

A low frequency, high Bsat power material optimized for use in line output transformers at frequencies up to 0.2 MHz.

SYMBOL	CONDITIONS	VALUE	UNIT
μ_i	25 °C; ≤ 10 kHz; 0.25 mT	2100 $\pm 20\%$	
μ_a	100 °C; 25 kHz; 200 mT	5000 $\pm 25\%$	
B	25 °C; 10 kHz; 1200 A/m 100 °C; 10 kHz; 1200 A/m	≈ 500 ≈ 440	mT
P _V	100 °C; 25 kHz; 200 mT 100 °C; 100 kHz; 100 mT 100 °C; 100 kHz; 200 mT	≤ 80 ≤ 80 ≈ 450	kW/m ³
ρ	DC; 25 °C	≈ 2	Ωm
T _C		≥ 240	°C
density		≈ 4800	kg/m ³



Material specification

3C30




Fig.4 Amplitude permeability as a function of peak flux density.




Fig.5 Reversible permeability as a function of magnetic field strength.




Fig.6 Specific power loss as a function of peak flux density with frequency as a parameter.




Fig.7 Specific power loss for several frequency/flux density combinations as a function of temperature.

Material specification

3C30




DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype		These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in		These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support		These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.