

DATA SHEET

3H3 Material specification

Supersedes data of February 2002

2004 Sep 01

Material specification

3H3

3H3 SPECIFICATIONS

A low frequency filter material optimized for frequencies up to 0.2 MHz.

	CONDITIONS	VALUE	UNIT
μ_i	25 °C; ≤ 10 kHz; 0.25 mT	$2000 \pm 20\%$	
B	25 °C; 10 kHz; 1200 A/ m	≈ 360	mT
	100 °C; 10 kHz; 1200 A/ m	≈ 270	
$\tan\delta/\mu_i$	25 °C; 0.25 mT; 30 kHz	$\leq 1.6 \times 10^{-6}$	
	25 °C; 0.25 mT; 100 kHz	$\leq 2.5 \times 10^{-6}$	
η_B	25 °C; 100 kHz; 1.5 to 3 mT	$\leq 0.6 \times 10^{-3}$	T^{-1}
D_F	0.25 mT; 10 kHz: 25 °C	$\leq 3 \times 10^{-6}$	
	40 °C	$\leq 3 \times 10^{-6}$	
α_F	≤ 10 kHz; 0.25 mT;		K^{-1}
	5 to 25 °C	$(0.7 \pm 0.3) \times 10^{-6}$	
	25 to 55 °C	$(0.7 \pm 0.3) \times 10^{-6}$	
	25 to 70 °C	$(0.7 \pm 0.3) \times 10^{-6}$	
ρ	DC; 25 °C	≈ 2	Ωm
T_C		≥ 160	°C
density		≈ 4700	kg/m^3




Fig.1 Complex permeability as a function of frequency.




Fig.2 Initial permeability as a function of temperature.




Fig.3 Typical B-H loops.

Material specification

3H3




DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype		These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in		These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support		These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.