


# EP5 - a new telecom core size



**FERROXCUBE**  
A YAGEO COMPANY


# EP5 - a new telecom core size

In modern Telecom applications like ISDN and DSL ferrite-cored pulse and wideband transformers play an important role. These transformers provide impedance matching and safety isolation in modems placed between networks and telephone sets or computers. Driven by miniaturization, equipment manufacturers design-in the smallest possible transformers while still fulfilling the requirements set by chip-set makers or standardization bodies like ITU-T.

For pulse transformers (ISDN) a high  $L_p$  is of prime importance to keep pulses within the prescribed mask, so cores with high  $A_L$  values in high permeability materials like our 3E6 are often used. With these cores the number of turns, and thus parasitic capacitance, is kept low for improved high frequency behavior.

In DSL applications the key design parameter is THD (Total Harmonic Distortion). It must be kept low to avoid bit errors during the translation of analog signals to digital information. The new low-THD material 3E55 is therefore ideal for use in DSL transformers and thus precision gapped products are offered.

EP cores are very popular for these designs because of their flat top for easy handling and their closed shape for excellent magnetic shielding. Up to now the EP7 core was the smallest available size in the range. For this reason, designers requiring smaller sizes had to deviate from normal practice and switch to small E cores or toroids.



# New material 3E55 with improved THD properties

The THD of a ferrite component should be low under operating conditions. THD is a function of flux density (B), frequency (f) and temperature (T). To evaluate material quality with respect to THD,  $V_1$  and  $V_3$  have been measured with an audio analyzer on toroid samples together with their amplitude permeability  $\mu_a$ . In the curves of Fig.1, 8 and 9 the behaviour of  $\text{THD}/\mu_a$  as a function of B, T, and f is shown for the current high permeability ferrite 3E6 ( $\mu_i = 10.000$ ) and for the newly developed low THD material 3E55. Values are plotted in dB-units calculated with the formula:

$$20 \cdot \log(V_3/V_1) / (\mu_a)$$

As expected THD increases when the flux density level rises (Fig. 1.) This can be explained by the fact that pores and impurities inside the material act as pinning points for the domain-wall movement. At a certain magnetic field strength (H) the domain-walls jump to the next pinning point. Such irreversible jumps result in a more than linear increase of the flux density B with field H, resulting in distortion. Ferrite materials having an improved, clean homogeneous microstructure will allow a "gentle" move of the domain walls with the driving field, resulting in a more linear behaviour. The newly developed material 3E55 is optimized by raw material choice, (low impurity level), addition of dopes and improved sinter conditions. This results in an improvement for flux densities up to 20 mT.




In the temperature behaviour of every ferrite a minimum for  $\text{THD}/\mu_a$  is noticed. This minimum coincides with the point where the permeability versus temperature shows a (secondary) maximum denoted as Tsm. At this temperature the anisotropy and therefore hysteresis losses are minimal. To the left and right of this temperature the THD usually increases sharply. Changes in chemical composition of the material will shift the curie temperature  $T_c$  and the Tsm of the material. Materials optimized for THD show low values over a substantial temperature range and not for one or two specific temperatures. The optimum is found by placing the  $T_c$  slightly above 100 °C and the Tsm at about 5 °C.

Fig. 3 shows the improvement in THD performance over the temperature range for 3E55 compared to 3E6.


These results are based on measurements on toroids. For the THD in core sets not only the properties of the pure material but also the condition of the mating surfaces in the core set determine the overall distortion in the product. Bad planarity or grinding grooves will cause magnetic flux concentrations, which increases the distortion level, especially when the surfaces are directly in contact with each other. Coarse- and fine-ground samples show inferior distortion compared to lapped samples. However this difference disappears when an airgap is introduced by putting a spacer between the core halves.

## Ferrite material properties

The curves clearly show the differences in material characteristics between "normal" high permeability ferrites and the new low distortion material 3E55. Notice the improved behaviour of THD at low flux densities and as a function of temperature. However, at room temperature and higher flux densities ( $B > 30$  mT), the differences between 3E55 and 3E6 are not significant.








The new EP5 design, complete with SMD bobbin and clip satisfies the need for smaller pulse transformers. They are available in the high permeability material 3E6 for pulse transformers and in the new low harmonic distortion material 3E55 for DSL wideband applications.

Even though the EP5 has half the volume of an EP7 it is suitable to build pulse transformers which comply to CCITT (G.703).

***Direct replacement for E5.3 cores***

EP5 can serve as a direct replacement for a wideband transformer based on E5.3 because their bobbins have the same footprint. Advantages of the EP5 design compared to E5.3 are: improved magnetic shielding due to the closed core shape, higher  $A_L$  values and a larger winding area. Furthermore, it can be shown that the EP core shape intrinsically has a superior THD performance. This is explained in more detail in our Application Note "The use of Ferrite Cores in DSL wideband Transformers" (9398 088 00111).

# The EP5 product range




## CORE SETS

### Effective core parameters

SYMBOL	PARAMETER	VALUE	UNIT
$\Sigma(l/A)$	core factor (C1)	3.20	mm <sup>-1</sup>
$V_e$	effective volume	28.7	mm <sup>3</sup>
$l_e$	effective length	9.70	mm
$A_e$	effective area	3.00	mm <sup>2</sup>
$A_{min}$	minimum area	2.27	mm <sup>2</sup>
$m$	mass of core set	≈ 0.5	g

## Core sets

MATERIAL	$A_L$ (nH)	EFFECTIVE PERMEABILITY ( $\mu_e$ )	AIRGAP ( $\mu$ m)	TYPE NUMBER
3E55	16 ± 3%	≈ 41	≈ 320	EP5-3E55-A16
	25 ± 3%	≈ 64	≈ 170	EP5-3E55-A25
	40 ± 5%	≈ 102	≈ 90	EP5-3E55-A40
	63 ± 8%	≈ 160	≈ 50	EP5-3E55-A63
	2000 +40/-30%	≈ 5100	≈ 0	EP5-3E55
3E6	2200 +40/-30%	≈ 5600	≈ 0	EP5-3E6



Clip for EP5  
Material: CrNi steel  
thickness 0,15 mm.

## General data for EP5 bobbin with 6 soldering pads

	SPECIFICATION
Coil former material	Liquid crystal polymer (LCP), glass reinforced, flame retardant in accordance with UL 94V-0; UL file number E54705(M)
Pin material	copper-tin alloy (CuSn), tin-lead alloy (SnPb) plated
Maximum operating temperature	155 °C, IEC 85 class F
Resistance to soldering heat	"IEC 68-2-20", Part 2, Test Tb, method 1B: 350°C, 3.5 s
Solderability	"IEC 68-2-20", Part 2, Test Ta, method 1: 235°C, 2 s

## Winding data for EP5 bobbin with 6 soldering pads

NUMBER OF SECTIONS	WINDING AREA (mm <sup>2</sup> )	MINIMUM WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	TYPE NUMBER
1	1.89	2.7	10.5	CPHS-EP5-1S-6P

# FERROXCUBE - your global partner

**Australia:** Contact Ferroxcube Taiwan  
Tel: +886 2 86650099, Fax: +886 2 86650145

**Austria:** Contact Ferroxcube Germany  
Tel: +49 (040) 527 28 305, Fax: +49 (040) 527 28 306

**Benelux:** Ferroxcube Netherlands, EINDHOVEN  
Tel: +31 (0)40 27 24 216, Fax: +31 (0)40 27 24 411

**Canada:** Contact Ferroxcube USA  
Tel: +1 877 433 7748, Fax: +1 770 992 0725

**China:** Ferroxcube Hong Kong, SHANGHAI  
Tel: +86 21 3308 0065, Fax: +86 21 3308 0095

**Czech Republic:** Contact Ferroxcube Germany  
Tel: +49 (040) 527 28 305, Fax: +49 (040) 527 28 306

**Denmark:** Contact Ferroxcube Sweden  
Tel: +46 (8) 5985 2427, Fax: +46 (8) 5985 2795

**Finland:** Contact Ferroxcube Sweden  
Tel: +46 (8) 5985 2427, Fax: +46 (8) 5985 2795

**France:** Ferroxcube France, SURESNES  
Tel: +33 (01) 4099 6598, Fax: +33 (01) 4099 6048

**Germany:** Ferroxcube Germany, HAMBURG  
Tel: +49 (040) 527 28 302, Fax: +49 (040) 527 28 306

**Greece:** Contact Ferroxcube Italy  
Tel: +39 203 5932, Fax: +39 203 6842

**Hungary:** Contact Ferroxcube Germany  
Tel: +49 (040) 527 28 305, Fax: +49 (040) 527 28 306

**Hong Kong:** Ferroxcube Hong Kong, HONG KONG  
Tel: +852 2319 2740, Fax: +852 2319 2757

**Indonesia:** Contact Ferroxcube Singapore  
Tel: +65 258 2723, Fax: +65 251 1952

**Ireland:** Contact Ferroxcube UK  
Tel: +44 1306 512 040, Fax: +44 1306 512 343

**Israel:** Arrow/Rapac Ltd., TEL AVIV  
Tel: +972 3 6450 319, Fax: +972 3 6491 007

**Italy:** Ferroxcube Italy, MONZA  
Tel: +39 203 5932, Fax: +39 203 6842

**Malaysia:** Contact Ferroxcube Singapore  
Tel: +65 258 2723, Fax: +65 251 1952

**Mexico:** Contact Ferroxcube USA  
Tel: +1 877 433 7748, Fax: +1 770 992 0725

**New Zealand:** Contact Ferroxcube Taiwan  
Tel: +886 2 86650099, Fax: +886 2 86650145

**Norway:** Contact Ferroxcube Sweden  
Tel: +46 (8) 5985 2427, Fax: +46 (8) 5985 2795

**Philippines:** Contact Ferroxcube Singapore  
Tel: +65 258 2723, Fax: +65 251 1952

**Poland:** Contact Ferroxcube Germany  
Tel: +49 (040) 527 28 305, Fax: +49 (040) 527 28 306

**Portugal:** Contact Hispano Ferritas, Spain  
Tel: +34 (93) 270 40 57, Fax: +34 (93) 301 67 66

**Singapore:** Ferroxcube Singapore, SINGAPORE  
Tel: +65 258 2723, Fax: +65 251 1952

**Spain:** Hispano Ferritas, BARCELONA  
Tel: +34 (93) 270 40 57, Fax: +34 (93) 301 67 66

**Sweden:** Ferroxcube Sweden, STOCKHOLM  
Tel: +46 (8) 5985 2427, Fax: +46 (8) 5985 2795

**Switzerland:** Contact Ferroxcube Germany  
Tel: +49 (040) 527 28 305, Fax: +49 (040) 527 28 306

**Taiwan:** Ferroxcube Taiwan, TAIPEI  
Tel: +886 2 86650099, Fax: +886 2 86650145

**Turkey:** Contact Ferroxcube Italy  
Tel: +39 203 5932, Fax: +39 203 6842

**United Kingdom:** Ferroxcube UK, DORKING  
Tel: +44 1306 512 040, Fax: +44 1306 512 343

**United States:** Ferroxcube USA, ROSWELL (GA)  
Tel: +1 877 433 7748, Fax: +1 770 992 0725

**For all other countries apply to closest regional sales office:**

■ HAMBURG, Germany  
Tel: +49 (040) 527 28 302, Fax: +49 (040) 527 28 306

■ ROSWELL (GA), USA  
Tel: +1 877 433 7748, Fax: +1 770 992 0725

■ TAIPEI, Taiwan  
Tel: +886 2 86650099, Fax: +886 2 86650145

© Ferroxcube International Holding B.V. 2001

All rights are reserved. Reproduction in whole or in part is prohibited without the prior written consent of the copyright owner.  
The information presented in this document does not form part of any quotation or contract, is believed to be accurate and reliable and may be changed without notice.  
No liability will be accepted by the publisher for any consequence of its use. Publication thereof does not convey nor imply any license under patent- or other industrial or intellectual property rights.

Visit our web-site for the latest information on new products, application info as well as updated phone- and fax numbers

**Internet:** [www.ferroxcube.com](http://www.ferroxcube.com)

Printed in The Netherlands

9398 288 00211

Date of release: May 2001



**FERROXCUBE**  
A YAGEO COMPANY