FERROXCUBE

DATA SHEET

P11/7 P cores and accessories

Supersedes data of February 2002

2004 Sep 01




P11/7

P cores and accessories

CORE SETS

Effective core parameters

SYMBOL	PARAMETER	VALUE	UNIT
Σ(I/A)	core factor (C1)	0.956	mm ⁻¹
V _e	effective volume	251	mm ³
l _e	effective length	15.5	mm
A _e	effective area	16.2	mm ²
A _{min}	minimum area	13.2	mm ²
m	mass of set	≈ 1.8	g



Core sets for filter applications

Clamping force for A_L measurements, 35 $\pm 10\ N.$

GRADE	A _L (nH)	$\mu_{\mathbf{e}}$	AIR GAP (μm)	TYPE NUMBER (WITH NUT)	TYPE NUMBER (WITHOUT NUT)
3D3 sup	16 ±3%	≈ 12	≈ 2210	P11/7-3D3-E16/N	P11/7-3D3-E16
	25 ±3%	≈ 19	≈ 1280	P11/7-3D3-E25/N	P11/7-3D3-E25
	40 ±3%	≈ 31	≈ 710	P11/7-3D3-E40/N	P11/7-3D3-E40
	63 ±3%	≈ 48	≈ 400	P11/7-3D3-E63/N	P11/7-3D3-E63
	100 ±3%	≈ 76	≈ 220	P11/7-3D3-A100/N	P11/7-3D3-A100
	800 ±25%	≈ 610	≈ 0	_	P11/7-3D3
3H3 sup	160 ±3%	≈ 122	≈ 140	P11/7-3H3-A160/N	P11/7-3H3-A160
	250 ±3%	≈ 190	≈ 80	P11/7-3H3-A250/N	P11/7-3H3-A250
	1650 ±25%	≈ 1260	≈ 0	_	P11/7-3H3

Core sets for general purpose transformers and power applications

Clamping force for A_L measurements, 35 ± 10 N.

GRADE	A _L (nH)	μ _e AIR GAP (μm)		TYPE NUMBER
3C81	100 ±3%	≈ 76	≈ 240	P11/7-3C81-A100
	160 ±3%	≈ 122	≈ 140	P11/7-3C81-A160
	250 ±3%	≈ 190	≈ 85	P11/7-3C81-A250
	2050 ±25%	≈ 1560	≈ 0	P11/7-3C81

P11/7

GRADE	A _L (nH)		AIR GAP (μm)	TYPE NUMBER
3C91 des	2050 ±25%	≈ 1 560	≈ 0	P11/7-3C91
3F3	100 ±3%	≈ 76	≈ 240	P11/7-3F3-A100
	160 ±3%	≈ 122	≈ 140	P11/7-3F3-A160
	250 ±5%	≈ 190	≈ 80	P11/7-3F3-A250
	1650 ±25%	≈ 1260	≈ 0	P11/7-3F3

Core sets of high permeability grades

Clamping force for A_L measurements, 35 $\pm 10~\mbox{N}.$

GRADE	A _L (nH)	$\mu_{\mathbf{e}}$	AIR GAP (μm)	TYPE NUMBER
3E27	3400 ±25%	≈ 2600	≈ 0	P11/7-3E27

Properties of core sets under power conditions

	B (mT) at	CORE LOSS (W) at					
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 100 kHz; B = 200 mT; T = 100 °C	f = 400 kHz; B = 50 mT; T = 100 °C		
3C81	≥320	≤ 0.05	_	_	_		
3C91	≥315	_	≤ 0.015 ⁽¹⁾	≤ 0.12 ⁽¹⁾	_		
3F3	≥315	-	≤ 0.03	-	≤ 0.05		

Note


1. Measured at 60 °C.

P11/7

INDUCTANCE ADJUSTERS

General data

PARAMETER	SPECIFICATION
Material of head and thread	polypropylene (PP), glass fibre reinforced
Maximum operating temperature	125 °C



Inductance adjuster selection chasup (applies to all types)

GRADE	A _L (nH)	TYPES FOR LOW ADJUSTMENT	Δ L/L ⁽¹⁾	TYPES FOR MEDIUM ADJUSTMENT	Δ L/L ⁽¹⁾	TYPES FOR HIGH ADJUSTMENT	Δ L/L ⁽¹⁾
3H3	100	_	_	ADJ-P9/P11-YELLOW	13	ADJ-P9/P11-BROWN	24
	160	ADJ-P9/P11-YELLOW	8	ADJ-P9/P11-BROWN	15	ADJ-P9/P11-GREY	22
	250	ADJ-P9/P11-BROWN	9	ADJ-P9/P11-GREY	14	_	_
3D3	16	_	_	ADJ-P9/P11-YELLOW	19	_	_
	25	_	_	_	-	ADJ-P9/P11-YELLOW	30
	40	_	_	_	-	ADJ-P9/P11-YELLOW	24
	63	_	_	ADJ-P9/P11-YELLOW	18	_	_
	100	_	_	ADJ-P9/P11-YELLOW	11	_	_

Note


1. Maximum adjustment range.

2004 Sep 01

COIL FORMERS

General data CP-P11/7-1S coil former

PARAMETER	SPECIFICATION
Coil former material	polybutyleneterephtalate (PBT), glass reinforced, flame retardant in accordance with "UL 94V-0"; UL file number E45329 (R)
Maximum operating temperature	155 °C, "IEC 60085", class F




Winding data for CP-P11/7-1S coil former

NUMBER SECTION	_	WINDING AREA (mm²)	MINIMUM WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	TYPE NUMBER
1		4.8	3.1	22.6	CP-P11/7-1S

General data for CP-P11/7-A coil former

PARAMETER	SPECIFICATION	
Coil former material	acetal (POM), glass reinforced, flame retardant in accordance with "UL 94-HB"; UL file number E66288(R)	
Maximum operating temperature	105 °C	



Winding data for CP-P11/7-A coil former

NUMBER OF SECTIONS	MINIMUM WINDING AREA (mm²)	NOMINAL WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	TYPE NUMBER
2	2×2.00	2 × 1.52	22.7	CP-P11/7-2S-A
3	3×1.16	3 × 0.91	22.7	CP-P11/7-3S-A ⁽¹⁾

6

Note

1. UL file number E93370(M).

2004 Sep 01


P11/7

P cores and accessories

MOUNTING PARTS


General data


ITEM	REMARKS	FIGURE	TYPE NUMBER
Tag plate	material: phenolformaldehyde (PF), glass reinforced	5	TGP-P11/7-4P
	flame retardant: in accordance with "UL 94V-0"; file number E167521(M)		
	maximum operating temperature: 180 °C, "IEC 60085", class H		
	pins: copper-tin alloy (CuSn), tin-lead alloy (SnPb) plated		
	resistance to soldering heat in accordance with "IEC 60068-2-20", Part 2, Test Tb, method 1B: 350 °C, 3.5 s		
	solderability in accordance with "IEC 60068-2-20", Part 2, Test Ta, method 1: 235 °C, 2 s		
Container	copper-zinc alloy (CuZn), SnPb-plated, transition to lead-free (Sn) ongoing	6	CON-P11/7
	earth pins: presoldered		
Spring	CrNi-steel	7	SPR-P11/7
	spring force: ≈35 N when mounted		
Clamp	spring steel, tin-plated	7 CLM/TP-P11/7	




P11/7

P cores and accessories







P11/7

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.