

DATA SHEET

TX36/23/10
Ferrite toroids

Supersedes data of February 2002

2004 Sep 01

Ferrite toroids

TX36/23/10

RING CORES (TOROIDS)

Effective core parameters


SYMBOL	PARAMETER	VALUE	UNIT
$\Sigma(l/A)$	core factor (C1)	1.38	mm^{-1}
V_e	effective volume	5820	mm^3
l_e	effective length	89.7	mm
A_e	effective area	64.9	mm^2
m	mass of core	≈ 27	g

Coating

The cores are coated with epoxy, flame retardant in accordance with "UL 94V-0"; UL file number E 228348. The colour is white.

Isolation voltage

DC isolation voltage: 2000 V.
Contacts are applied on the edge of the ring core, which is also the critical point for the winding operation.



Ring core data

GRADE	A_L (nH)	μ_i	TYPE NUMBER
4C65	$112 \pm 25\%$	≈ 125	TX36/23/10-4C65
3C90 des	$2060 \pm 25\%$	≈ 2300	TX36/23/10-3C90
3C81	$2455 \pm 20\%$	≈ 2700	TX36/23/10-3C81
3C11	$3900 \pm 25\%$	≈ 4300	TX36/23/10-3C11
3E27	$4545 \pm 20\%$	≈ 5000	TX36/23/10-3E27
3E6 des	$9090 \pm 30\%$	≈ 10000	TX36/23/10-3E6

Properties of cores under power conditions

GRADE	B (mT) at	CORE LOSS (W) at	
	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C
3C90	≥ 320	≤ 0.64	≤ 0.64
3C81	≥ 320	≤ 1.1	—

Ferrite toroids

TX36/23/10

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype		These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in		These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support		These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.