

DATA SHEET

TX55/32/18
Ferrite toroids

Supersedes data of February 2002

2004 Sep 01

Ferrite toroids

TX55/32/18

RING CORES (TOROIDS)

Effective core parameters


SYMBOL	PARAMETER	VALUE	UNIT
$\Sigma(l/A)$	core factor (C1)	0.651	mm^{-1}
V_e	effective volume	26580	mm^3
l_e	effective length	132	mm
A_e	effective area	202	mm^2
m	mass of core	≈ 134	g

Coating

The cores are coated with epoxy, flame retardant in accordance with "UL 94V-0"; UL file number E 228348. The colour is white.

Isolation voltage

DC isolation voltage: 2000 V.
Contacts are applied on the edge of the ring core, which is also the critical point for the winding operation.



Ring core data

GRADE	A_L (nH)	μ_i	TYPE NUMBER
4A11	$1640 \pm 25\%$	$\approx 700^{(1)}$	TX55/32/18-4A11
3C11	$8300 \pm 25\%$	≈ 4300	TX55/32/18-3C11
3E25	$10620 \pm 25\%$	≈ 5500	TX55/32/18-3E25
3E27	$10620 \pm 25\%$	≈ 5500	TX55/32/18-3E27

1. Old permeability specification maintained.

Ferrite toroids

TX55/32/18




DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype		These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in		These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support		These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.